

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 March 2005 (24.03.2005)

PCT

(10) International Publication Number
WO 2005/027158 A2

(51) International Patent Classification⁷: **H01G**
(21) International Application Number:
PCT/JP2004/013575

(22) International Filing Date:
10 September 2004 (10.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2003-319875 11 September 2003 (11.09.2003) JP

(71) Applicants (for all designated States except US): **HONDA MOTOR CO., LTD.** [JP/JP]; 1-1, Minami-Aoyama 2-chome, Minato-ku, Tokyo 107-8556 (JP). **KURARAY CHEMICAL CO., LTD.** [JP/JP]; 4342, Tsurumi, Bizen-shi, Okayama 705-0025 (JP). **KASHIMA OIL CO., LTD.** [JP/JP]; 10-1, Toranomon 2-chome, Minato-ku, Tokyo 105-0001 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FUJINO, Takeshi**

[JP/JP]; c/o Honda R & D Co., Ltd., 4-1, Chuo 1-chome, Wako-shi, Saitama 351-0193 (JP). **NISHIMURA, Shushi** [JP/JP]; c/o Kuraray Chemical Co., Ltd, 4342, Tsurumi, Bizen-shi, Okayama 705-0025 (JP).


(74) Agents: **OGURI, Shohei** et al.; Eikoh Patent Office, Ark Mori Building, 13th Floor, 12-32, Akasaka 1-chome, Minato-ku, Tokyo 107-6013 (JP).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

[Continued on next page]

(54) Title: PROCESS OF PRODUCING ACTIVATED CARBON FOR ELECTRODE OF ELECTRIC DOUBLE LAYER CAPACITOR



(57) Abstract: A process for producing an activated carbon for an electrode of an electric double-layer capacitor, includes a step of subjecting a carbonized material to an alkali activating treatment, wherein the carbonized material has an average true specific gravity of 1.450 to 1.650 and a variation of the true specific gravities of 0.025 or less.



FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

- *without international search report and to be republished upon receipt of that report*